

STATE**OF****TENNESSEE**

(Rev. 5-18-15)

January 1, 2015

Supplemental Specifications - Section 900**of the****Standard Specifications for Road and Bridge Construction****January 1, 2015****Subsection 903.01 - Table 903.01-1 (pg. 920) , 5-18-15; Replace Note (1) with the following:**

“(1) If the fine aggregate is manufactured from crushed stone and if material finer than the No. 200 sieve consists of the dust of fracture, essentially free from clay or shale, this limit may be increased to 5%.

Subsection 903.05 – B. Type B Aggregate (pg. 927), 5-18-15; Replace 3. With the following:

“Do not use material having a clay content greater than 12%, as determined by hydrometer analysis performed in accordance with AASHTO T 88. Material may be used having a clay content exceeding 12% if a plasticity index-fines product does not exceed 3 when calculated by the following formula:

Subsection 903.11 (pg. 934), 5-18-15; A. Coarse Aggregate (retained on a No. 4 sieve) Replace with the following: “2. Material retained on the No. 4 sieve shall contain a maximum of 10% elongated pieces (length greater than five times the average thickness)”

Subsection 903.24 (pg. 946), 5-18-15; Modify the following, “Provide coarse aggregate consisting of crushed gravel, crushed granite, crushed slag, crushed quartzite, crushed gneiss, or crushed sandstone. Other crushed aggregate may be used provided it has the chemical, physical, and performance characteristics specified in Table 903.24-1.”

Subsection 904.01 (pg 955-956) 5-27-15; Modify the following:

“Only obtain asphalt cement for use on Department projects from Certified Asphalt Cement Suppliers that have an approved Quality Control Plan in accordance with the Department’s Standard Operating Procedures.

Asphalt cement shall conform to AASHTO M 320 and Department procedures. Direct Tension testing is not required.

Instead of PG 64-22, the Contractor may use asphalt cement graded to PG 67-22. PG 67-22 shall conform to the requirements of AASHTO M 320 when the applicable tests are conducted at 67 °C and -12 °C, and the dynamic shear of the rolling thin film, pressure aged vessel sample is tested at 26.5 °C.

To modify the asphalt cement high-temperature grade properties, properly blend styrene butadiene (SB), styrene butadiene styrene (SBS), or styrene butadiene rubber (SBR) to a PG 64-22 or PG 67-22 base asphalt.

In addition to the above requirements, asphalt cements shall meet the requirements specified in Table 904.01-1.

Table 904.01-1: Requirements for Asphalt Cement

Property*	PG 64-22, PG 67-22	PG 70-22	PG 76-22	PG 82-22
Non-recoverable creep compliance at 3.2kPa, J _{nr} (3.2), kPa ⁻¹ at 64°C, Max	4.5	1.0	0.5	0.5
% Difference in Non-Recoverable Creep Compliance, J _{nr} (diff) at 64°C, %, Max	75	75	75	75

* Tested in accordance with AASHTO T350.

All modified grades shall meet the requirements for Indication of Elastic response as defined in Appendix X1 of AASHTO M332.

Furnish a certification to the Engineer on each project stating that the asphalt cement provided meets the Department's specification. Ensure that quality control and compliance testing are completed in accordance with the asphalt supplier's approved quality control plan and Department procedures.

In addition, the asphalt cement supplier shall provide a temperature-viscosity curve for PG 64-22 and PG 67-22 asphalt cements with a recommended mixing temperature range. In order to develop a temperature-viscosity curve, it may be necessary to run the viscosity test at a higher temperature, based on the softening point of the modified asphalt cement.

Subsection 904.03 (pg.954), 5-18-15; Replace with the following:

Subsection 904.03, Table 904.03-1(c). Modify as follows for TTT-1:

Table 904.03-1(c): Test Requirements for Emulsified Asphalt

Practices	AASHTO Test Method	CRS-2P	RS-2	RS-1	TTT-1	TTT-2
Saybolt-Furol Viscosity @ 77 °F, seconds	T59	n/a	n/a	20-100	20-100	10-100
Saybolt-Furol Viscosity @ 122 °F, seconds	T59	100-400	75-400	n/a	n/a	n/a
Storage Stability Test, 24- h, %	T59	1 Max	1 Max	1 Max	1 Max	1 Max
5-day Settlement, %	T59	n/a	n/a	n/a	n/a	n/a
Particle Charge	T59	Positive	n/a	n/a	n/a	Positive
Sieve Test, %	T59	0.1 Max	0.1 Max	0.1 Max	0.1 Max	0.1 Max
Residue by	T59	<i>Evaporation</i>	Distillation	Distillation	Distillation	Distillation ⁽¹⁾
Residue, %	T59	65 Min	63 Min	55 Min	50 Min	50 Min
Demulsibility, %	T59	40 Min	60 Min	60 Min	n/a	n/a
Distillate, %	T59	n/a	n/a	n/a	n/a	n/a
Oil Test, %	T59	n/a	n/a	n/a	n/a	n/a
Stone Coating	T59	n/a	n/a	n/a	n/a	n/a
Float Test, seconds	T50	n/a	n/a	n/a	n/a	n/a
Penetration	T49	75-175	100-200	100-200	0-20	40-90
Elastic Recovery, % ⁽²⁾	T301	50 Min	n/a	n/a	n/a	n/a
Ductility @ 77 °F, cm	T51	40 Min	40 Min	40 Min	n/a	n/a
Ductility @ 40 °F, cm	T51	n/a	n/a	n/a	n/a	n/a
R&B Softening Point, °F	T53	125 Min	n/a	n/a	60-75	n/a
Original G*/sind @ 82 °C	T315	n/a	n/a	n/a	1.0 Min	n/a

⁽¹⁾ Distill at 350 °F⁽²⁾ Straight-sided mold, 20-cm elongation, 5min hold, 25 °C

Subsection 908.04 (pg. 968) , 5-26-15, High Strength Bolts, A. Specifications; Add the following to the first paragraph:

“Unless otherwise shown on the Plans, mechanically galvanize all bolts, nuts and washers in accordance with ASTM B695 Class 50.”

Subsection 921.01 (pg. 1049), 5-18-15, Water; Replace with the following:

For mixing concrete, use water that is reasonably clean and free of oil, salt, acid, alkali, sugar, vegetable matter, and other substances injurious to the finished product. Water provided by a municipal utility may be used without testing.

All other water shall have quality results submitted in accordance with the frequency listed in Table 921.01-01. All water quality results shall adhere to Table 921.01-2.

Table 921.01-1 Testing Frequency for Mixing Water

Water Source	Testing Frequency ⁽¹⁾
Municipal	NA
Non-Municipal	Every 3 months; tested annually after 4 consecutive passing tests

(1) The frequency may vary at the discretion of the Department.

Table 921.01-2 Quality Requirements for Mixing Water

Maximum Concentration in Mixing Water	Limits	ASTM Test Method ⁽¹⁾
Chloride Ion Content, ppm	500	C114
Alkalies as (NaO2 + 0.658 K2O), ppm	600	C114
Sulfates as SO4, ppm	3000	C114
Total Solids by mass, ppm	50000	C1603
pH	4.5-8.5	⁽²⁾
Resistivity, Minimum, kohm-cm	0.500	D1125
Soluble Carbon Dioxide, ppm	600	D513
Calcium and Magnesium, ppm	400	D511
Iron, ppm	20	⁽²⁾
Phosphate, ppm	100	D4327

(1) Other methods (EPA or those used by water testing companies) are generally acceptable.

(2) No ASTM method available.